

JACKSUN - 18H

LOW HYDROGEN WELDING ELECTRODE FOR MILD & MEDIUM TENSILE STEELS

GRADES

AWS / SFA 5.1 E 7018
IS 814 EB 5426 H3 JX

CHARACTERISTICS

A basic coated, low hydrogen, iron powder type all position electrode, operates on both AC & DC. The slags are easily removable and the welds are of radiographic quality. The weld metal possesses good mechanical properties.

APPLICATIONS

An ideal electrode for all types of fabrication including heavy joints under restraint and joints subject to dynamic loading. Typical for pressure vessels, boilers, pipelines, ship building, wagons, coaches, earth moving equipments, atomic reactor shells, blast furnace steel work, penstocks, heavy machinery, cranes, tanks and vessels.

WELD CHEMISTRY

CARBON - 0.15% max	CHROMIUM - 0.2%
MANGANESE - 1.60% max	NICKEL - 0.3%
SILICON - 0.75% max	MOLYBDENUM - 0.3%
PHOSPHORUS - 0.035 max	VANADIUM - 0.08%
SULFUR - 0.035 max	

MECHANICAL PROPERTIES

TENSILE STRENGTH (N/mm²) - 510 - 610 MIN
YEILD STRENGTH (N/mm²) - 400 MIN.
ELONGATION (L-5d)% - 20 MIN.
CVN IMPACT @ 30°CJ - 27 AVG MIN

WELDING CURRENT

DC(+) / AC 70V

- * **2.00 mm** - 60 - 100 Amps
- * **3.15 mm** - 100 - 140 Amps
- * **4.00 mm** - 140 - 190 Amps
- * **5.00 mm** - 190 - 250 Amps

PACKING DATA

Size (mm)	1 BOX	1 CARTON
2.5 x 350	150 Pcs	4 Boxes (600 Pcs)
3.15 x 450	120 Pcs	4 Boxes (480 Pcs)
4 x 450	80 Pcs	4 Boxes (320 Pcs)
5 x 450	55 Pcs	4 Boxes (220 Pcs)

APPROVALS

**BIS, IBR, BHEL, IRS Gr.3 YHH, ABS Gr.3YH5, DNV Gr.3 YH5,
Ordnance Factory Medak, Cethar Vessels, APPGCL**

CONTACT

ROYAL WELDING WIRES PRIVATE LIMITED

An ISO 9001 - 2008 Certified Company

No. 7 Karanai Puducheri Village, (Via) Urapakkam - 603 202.

Kanchipuram Dist. Tamilnadu

Ph.: +91 9500055940 / 9500033041

E-mail : admin@theroyalfirm.in Web : www.theroyalfirm.in